

**HDPE BAG - 25KG CAPACITY FOR STABLE BLEACHING POWDER BAGS**

25KG STABLE BLEACHING POWDER  
BAGS  
HDPE CIRCULAR WOVEN LAMINATED  
BOTH SIDES WITH LDPE LINERS  
CAPACITY OF BAG: 25 KGS OF SBP  
HDPE BAGS (OUTER BAGS): -  
SIZE OF BAGS: 23 INCH X 30 INCH  
MESH: 10 X 10  
DENIER: 1000 APPX  
WEIGHT: 100 GMS (+/- 3%)  
BREAKING STRENGTH:  
    LENGTH WISE: 70 KGF  
    WIDTH WISE: 70 KGF  
THE ENLONGATION OF THE LAMINATED  
FABRICS SHALL NOT BE LESS THAN  
15 % AND MORE THAN 25%  
BOTTOM SEAM: 30 KGF  
FABRIC SHALL BE WOVEN FROM HDPE  
TAPES AND SHALL BE FREE FROM  
ALL MAJOR WEAVING DEFECTS LIKE  
PICK POINTS, MISSING TAPES,  
BIASNESS ETC.  
APPEARANCE OF BAG SHALL BE  
MILKY WHITE  
(SHALL BE USE CORRECT QTY  
AND QUALITY OF MASTER BATCH)  
BAGS SHALL HAVE BOTH SIDE  
CIRCULER LAMINATED OF VIRGIN  
QUALITY LDPE FILM  
(SHALL BE FREE FROM PINHOLES,  
POROSITY, TEARS, PATCHES,  
AIR POCKETS, BLISTERS OR ANY  
OTHER VISIBLE DEFECTS)  
THE BOTTOM OF THE BAG SHALL  
HAVE MIN. 25 MM FOLDING WHEN  
MEASURED FROM OUTSIDE.  
THE BOTTOM OF BAGS SHALL HAVE  
TWO-FOLD (6 LAYERS).  
DOUBLE SEALED BOTTOM / DOUBLE  
WITH HDPE THREADS  
LOOSE LINERS  
(INNER LINERS, BLACK & WHITE)  
INNER LINERS SHALL BE MADE  
FROM RELIANCE GRADE LDPE/  
LLDPE IN PROPORTION USE OF  
85% LLDP AND 15% LDPE  
SIZE OF BOTH LINERS  
    : 24 INCH X 38 INCH  
WEIGHT OF EACH LINER  
    : 80 GMS (+/- 3%)  
GUAGE OF EACH LINER: 250 GAUGE  
TENSILE STRENGTH: 0.025KG/CM2  
TEMP TO SUSTAIN: 80 DEG. C  
TOTAL WEIGHT OF BAGS  
(WITH BLACK AND WITH LINERS  
INSERTED): 250 GMS (MIN)  
BOTH LINER SHALL BE DELIVERED  
WITH INSERTED COMPLETELY AND  
PROPER IN HDPE BAGS  
\*ALL BAGS SHOULD HAVE TWO  
LINERS, OUTER BLACK AND INNER

TRANSPARENT WHITE  
PRINTING MATTER IN BLUE &  
GREEN COLOUR AND HAVING  
GACL LOGO AND ISI MARK\*  
BUNDLES MUST BE WITH GOOD  
PACKING AND SUSTAINABLE  
DURING HANDLING.