

LIQUID SODIUM ALUMINATE
NA₂AL₂O₄ % 41.0
AL₂O₃ % 25.5
FE % 0.0040
NA₂O/AL₂O₃ RATIO 1.28
TOTAL NA₂O % 19.9
FREE NA₂O 4.0
COLOR AMBER
VISCOSITY 770 CP @ 20 DEG.C.
SP.GRAVITY 1.55 @ 38 DEG.C.

Approx. Annual Requirement : 720 MT
Approx. Monthly Consumption: 60 MT