

ACTIVATED CARBON

MATERIAL SPECIFICATIONS

TECHNICAL SPECIFICATION :-

CPG LF 12 X 40

MOLASSES NUMBER :- 210 MIN

IODINE NUMBER (MG/G) :- 950 MIN

MOISTURE (%W/W) :- 3 MAX

ABRASION NUMBER :- 78 MIN

MEAN PARTICLE DIA (MM) :- 1.2 - 1.4

PH (EXTRACTABLE) - 5 TO 8

ACID SOLUBLE IRON (%W/W):- 0.01 MAX

ACID SOLUBLE ASH (%W/W):- 0.5 MAX

10 US MESH[2.00 MM](%W/W):- 5 MAX

<40 US MESH[0.425MM](PAN)(%W/W):-0.5 MAX