

TREATED ALUMINA

MATERIAL SPECIFICATIONS

CHEMICAL COMPOSITION

AL₂O₃ : 92.0%

NA₂O : 0.35 %

SIO₂ : 0.03 %

LOSS ON IGNITION (1000 DEG C)

MAX 8.0 %

PHYSICAL PROPERTIES

TOTAL PORE VOLUME

0.52 CC / GM

SURFACE AREA

380 M²/GM

BULK DENSITY

640 KG/M³

GRANULAR SIZE

8 X 14 MESH.

TOTAL ANNUAL QUANTITY : 280 MTS